






Acrisol®



Arcom d.o.o., Trgovsko podjetje, Hrastovec 7, 1236 OC Trzin
T: 01/5155 290, 5155 295; F: 01/5155 294; E: info@arcom.si; W: www.arcom.si

TECHNICAL FILE / TEHNIČNE LASTNOSTI	
COMPOSITION / SUROVINSKA SESTAVA:	100% Acrylic Dralon / 100% Akril Dralon
WIDTH / ŠIRINA:	160 cm
LENGTH OF ROLLS / DOLŽINA BALE:	50 lm / 50 tm
WEIGHT / TEŽA:	220 grs / m2 Acrisol standard:220 gr/m2 - Acrisol Caribe in Malibu: 280 gr/m2
FINISH/ ZAŠČITA TKANINE:	Water repellent / Vodoodbojni nanos
COLOR FASTNESS / BARVNA OBSTOJNOST:	
LIGHT FASTNES / OBSTOJNOST NA SVETLOBO: FASTNES TO RUBBING/ OBSTOJNOST NA DRGNJENJE: FASTNES TO CLORINATED WATER / OBSTOJNOST NA KLORIRANO VODO:	6-7 / 8 (UNE EN ISO 105-B02:2001 Metoda 5) 4-5 / 5 (UNE EN ISO 105-X12:2003) 5 / 5 (UNE EN ISO 105-E03:1997)
WATERPROOF RESULTS / VODOODBOJNE ZANČILNOSTI:	
WATER REPELLENCY / VODO ODBOJNOST: OIL REPELLENCY / OLJE ODBOJNOST:	6 / 6 (AATCC-193) 5 / 5 (AATCC-118)
PHYSICAL CHARACTERISTICS / FIZIKALNE LASTNOSTI :	
BREAKING STRENGHT / PRETRŽNA VREDNOST:	986 Warp / Osnova 525 Weft / Votek (UNE EN ISO 13936-1:1999)
RESISTANCE TO PILLING / ODPORNOST NA PILING:	4-5 / 5 (UNE EN ISO 12945-2:2001)
DIMENSIONAL CHANGE IN WASHING AND DRYING / KRČENJE TKANINE PRI PRANJU IN SUŠENJU:	-0,20% Warp / Osnova 0,00% Weft / Votek (UNE EN ISO 5077:2008)
ULTRA VIOLET PROTECTION / ZAŠČITA PRED UV ŽARKI:	50+ (AS/NZS 4399/1996)
TOLERANCE / OSTOPANJA:	Sensitive values of tolerance of +/-5%. Mogoča so minimalna vrednostna odstopanja podatkov iz tabele +/-5%
CLEANING ISTRUCTIONS/ NAVODILA ZA ČIŠČENJE:	    
APPLICATION / NAMEN UPORABE:	